



DEPARTMENT OF  
**ECOLOGY**  
State of Washington

# **Quality Assurance Project Plan**

---

## Phthalates and Metals in Children's Products

March 2012

Publication No. 12-07-023

## Publication Information

It is Washington State Department of Ecology policy to have an approved Quality Assurance Project Plan for all Agency-sponsored sampling events. The plan describes the objectives of the study and the procedures to be followed to achieve those objectives. After completing the study, Ecology will post a report of the study to the Internet.

The plan for this study is available on the Department of Ecology's website at <http://www.ecy.wa.gov/biblio/1207023.html>.

## Author and Contact Information

Alex Stone  
P.O. Box 47600  
Hazardous Waste and Toxics Reduction Program  
Washington State Department of Ecology  
Olympia, WA 98504-7600

For more information contact: Communications Consultant, phone 360-407-6834.

Washington State Department of Ecology - [www.ecy.wa.gov/](http://www.ecy.wa.gov/)

- Headquarters, Olympia 360-407-6000
- Northwest Regional Office, Bellevue 425-649-7000
- Southwest Regional Office, Olympia 360-407-6300
- Central Regional Office, Yakima 509-575-2490
- Eastern Regional Office, Spokane 509-329-3400

*Any use of product or firm names in this publication is for descriptive purposes only and does not imply endorsement by the author or the Department of Ecology.*

*To ask about the availability of this document in a format for the visually impaired, call 360-407-6834. Persons with hearing loss can call 711 for Washington Relay Service. Persons with a speech disability can call 877- 833-6341.*

# Quality Assurance Project Plan

---

## Phthalates and Metals in Children's Products

March 2012

### Approved by:

Signature:

Joshua Grice, Client, W2R Program

Date:

Signature:

John Williams, Client, W2R Program

Date:

Signature:

Alex Stone, Author/Project Manager, HWTR-HQ

Date:

Signature:

Ken Zarker, Author Supervisor, HWTR-HQ

Date:

Signature:

Samuel Iwenofu, HWTR Quality Assurance Officer

Date:

Signature:

Carol Kraege, Client, W2R Program

Date:

Signatures are not available on the Internet version.

HWTR-HQ: Hazardous Waste and Toxics Reduction Program

W2R: Waste 2 Resources Program

## Table of Contents

|  |     |
|--|-----|
| List of Figures and Tables.....                        | iii |
| Abstract.....  | iv  |
| Background.....  | 1   |
| Project Description.....                               | 2   |
| Sampling Process Design (Experimental Design).....     | 2   |
| Product Selection.....                                 | 2   |
| Product Screening.....                                 | 3   |
| Target Chemicals.....                                  | 3   |
| Organization and Schedule.....                         | 4   |
| Sample Collection and Preparation.....                 | 5   |
| Analytical Procedures.....                             | 7   |
| Budget.....  | 8   |
| Quality Objectives.....                                | 9   |
| Measurement Quality Objectives.....                    | 9   |
| Quality Control Procedures.....                        | 10  |
| Field.....   | 10  |
| Laboratory.....  | 10  |
| Data Management Procedures.....                        | 10  |
| Audits.....  | 10  |
| Report.....  | 10  |
| Data Verification.....                                 | 11  |
| Data Quality (Usability) Assessment.....               | 11  |
| References.....  | 12  |
| Appendix A. Chemicals of High Concern to Children..... | 13  |
| Appendix B. Glossary, Acronyms, and Abbreviations..... | 14  |

## List of Figures and Tables

### Figures

|                                    |   |
|------------------------------------|---|
| Figure 1. Niton Portable XRF ..... | 7 |
|------------------------------------|---|

### Tables

|   |    |
|---|----|
| Table 1. State and Federal Criteria for Analytes of Interest .....                    | 3  |
| Table 2. Specific Phthalate Esters Included in the Study .....                        | 4  |
| Table 3. Organization of Project Staff and Responsibilities .....                     | 4  |
| Table 4. Proposed Schedule for Completing Field and Laboratory Work and Reports ..... | 5  |
| Table 5. Niton Portable XRF LOQs and Expected Range of Results .....                  | 7  |
| Table 6. Laboratory Methods and Reporting Limits .....                                | 8  |
| Table 7. Project Budget.....  | 8  |
| Table 8. MQOs for Laboratory Analyses .....   | 9  |
| Table 9. Quality Control Tests.....   | 10 |

## Abstract

The Washington State Department of Ecology's (Ecology) Hazardous Waste and Toxics Reduction (HWTR) and Waste 2 Resources (W2R) Programs are conducting a study to evaluate presence of eight phthalates used as plasticizers and nine potentially hazardous metals in children's products. The study is being conducted to determine compliance with Washington's Children's Safe Product Act (CSPA) Legislation and to evaluate the level of phthalates and metals in children's products. It is being supported with funding from the Washington State Attorney General's Office.

Phthalates to be tested under this project include:

| <b>Phthalate ester</b>           | <b>CAS Number</b> |
|----------------------------------|-------------------|
| Diethyl phthalate (DEP)          | 84-66-2           |
| Dibutyl phthalate (DBP)          | 84-74-2           |
| Di-n-Hexyl Phthalate (DHP)       | 84-75-3           |
| Butyl Benzyl phthalate (BBP)     | 85-68-7           |
| Di-2-ethylhexyl phthalate (DEHP) | 117-81-7          |
| Di-n-octyl phthalate (DnOP)      | 117-84-0          |
| Diisodecyl phthalate (DIDP)      | 26761-40-0        |
| Diisononyl phthalate (DINP)      | 28553-12-0        |

Metals in this study include:

| <b>Metals</b> |            |
|---------------|------------|
| Antimony      | Lead       |
| Arsenic       | Mercury    |
| Cadmium       | Molybdenum |
| Cobalt        | Zinc       |
| Copper        |            |

It is Ecology policy to have an approved Quality Assurance Project Plan (QAPP) for all Agency-sponsored sampling events. The QAPP describes the objectives of the study and the procedures to be followed to achieve those objectives. After completion of the study, a report describing the study results will be posted to the Internet.

## Background

### Metals

Six metals (molybdenum, arsenic, cobalt, mercury, cadmium and antimony) were identified as Chemicals of High Concern to Children (CHCCs) as defined by the CSPA. Appendix A contains a list of all CHCCs identified in the CSPA. Lead levels in children's products were restricted by the CSPA to 90 ppm; however, subsequent passage of the Consumer Product Safety Improvement Act (CPSIA) Federal legislation substantially pre-empted the state lead limits. (CPSC, 2008) There are some some products for which the state level might remain pertinent; therefore, lead is added to the list of metals of concern.

The metals identified as CHCCs have been found to cause cancer (antimony, arsenic, cadmium and copper) and developmental impacts (molybdenum, arsenic, cadmium, cobalt and mercury). (DOH, 2010) In addition, they have been found in or likely to be found in children's products, which was required before they could be identified as CHCCs.

Two additional metals (copper and zinc) are also being analyzed in children's products. Copper and zinc have been identified as potentially having a major impact upon the Puget Sound (Ecology, 2011). Concerns have been raised about these metals in products as a potential source to the Puget Sound.

Copper and zinc are toxic to aquatic species and particularly the development of fish. As indicated in a report from the US Fish and Wildlife Services:

*Mixtures of zinc and copper are generally acknowledged to be more-than-additive in toxicity to a wide variety of aquatic organisms...*

The aquatic organisms impacted by zinc and copper include oysters and both marine and freshwater fish among others. (Eisler, 1993)

### Phthalates

Phthalates are a class of chemicals added to improve the flexibility of plastics. Phthalates are also used as solubilizing and stabilizing agents in other applications. Phthalates are used in a wide range of products including: adhesives, automotive plastics, detergents, lubricating oils, some medical devices and pharmaceuticals, plastic raincoats, solvents, vinyl tiles and flooring, and personal-care products, such as soap, shampoo, deodorants, lotions, fragrances, hair spray, and nail polish. Phthalates are often used in polyvinyl chloride type plastics, such as plastic bags, garden hoses, inflatable recreational toys, blood product storage bags, intravenous medical tubing, and toys (CDC, 2009).

As phthalates are not chemically bonded to the plastic, phthalates can be released directly to the environment. People can be exposed to phthalates through direct contact, through ingestion or through breathing of air contaminated with phthalates. Generally, phthalates are metabolized and excreted quickly and do not accumulate in the body (Anderson et al., 2001). The Center for

Disease Control and Prevention (CDC) found phthalates in most samples in its recent evaluation of toxic chemicals in humans. (CDC, 2009)

Eight phthalates and the phthalate precursor, phthalic anhydride, were identified as CHCCs in Ecology's rule to implement the CSPA. Of the eight phthalates, DEHP has been identified as causing cancer. All have been identified as having negative impacts on reproductivity, development or other systemic impacts. (DOH, 2010) In addition, DEHP has been identified as potentially having a major impact upon the Puget Sound. (Ecology, 2011)

## **Project Description**

Ecology's HWTR and W2R Programs will conduct a study to measure eight phthalates (see Table 2 for a list of the phthalate esters involved) and nine metals (antimony, arsenic, cadmium, cobalt, lead, molybdenum, zinc, copper and mercury) in children's products. The objective of the study will be to determine compliance with the state's CSPA legislation and to assess the levels of metals and phthalates in children's products.

Children's products will be purchased and screened for metals with a portable XRF analyzer during the spring and autumn of 2012. Those samples found to contain sufficient metals of interest will be sent to Manchester Environmental Laboratory for analysis. Samples containing phthalates will be sent to a contract laboratory for analysis.

## **Sampling Process Design (Experimental Design)**

Approximately 200 children's products will be gathered for testing during the two sampling events. Emphasis will be placed upon children's jewelry and other products from inexpensive stores. Products made of soft plastics will also be selected as they are more likely to contain phthalates and be reported on during the sampling period.

All product samples will be screened with a portable XRF for the metals of concern to determine if laboratory analysis is necessary. It is anticipated from the two sampling events that approximately 75 product samples will be forwarded for metals analysis and approximately 85 samples will be submitted for phthalate analysis. As an XRF cannot detect phthalates, information on the label, the type of plastic used and other potential sources of information will be used to determine whether a product sample is likely to contain any phthalates.

Items will be sent to the laboratory if they violate screening criteria (outlined below) during the XRF analysis or are selected for low level analysis. Laboratory analysis will be completed by inductively coupled plasma mass spectroscopy (ICP-MS) (metals), cold vapor atomic absorption (CVAA) (mercury), and gas chromatography-mass spectroscopy (GC/MS) (phthalates).

## **Product Selection**

Screening will focus on Tier 1 products and product components that are most likely to be mouthed or used by children under three. Under the CSPA Reporting Rule tiered approach, Tier 1 products are those intended to be put into a child's mouth, applied to their skin, or any

mouthable product for a child less than 3. Tier 1 products must be reported first. Tiers 2 – 4 include products intended for prolonged direct skin contact, short-duration direct skin contact, and no intended skin contact, respectively. Product analysis will be restricted to Tier 1 products for the samples collected in the spring unless sufficient samples cannot be obtained. Tier 2 products will be given priority for the samples collected in the autumn. Products in other Tiers will then be considered for analysis. For example, lip gloss and other cosmetic and personal care products that, when applied, are likely to be applied to the skin, ingested will be a higher priority than other children’s products. Products that are intended to be mouthed by children under 3, such as baby pacifiers, teething rings, and feeding products will also be given priority over other types of children’s products.

## Product Screening

Products will be screened using a portable X-Ray Fluorescence (XRF) gun following the XRF manufacturer’s recommendations and adaptations of ASTM method F 2617-08 *Standard Test Method for Identification and Quantification of Chromium, Bromine, Cadmium, Mercury, and Lead in Polymeric Material Using Energy Dispersive X-ray Spectrometry*. While ASTM method F 2617-08 is not intended for samples with surface coatings or non-polymeric materials, all samples will be screened following adaptations of the method for qualitative information.

## Target Chemicals

Target chemicals proposed for testing along with state and federal criteria are shown in Table 1 and the list of specific phthalate esters included in this study is found in Table 2.

**Table 1. State and Federal Criteria for Analytes of Interest**

| Analytes   | Action levels (ppm) |                    |
|------------|---------------------|--------------------|
|            | State <sup>=</sup>  | Federal            |
| Phthalates | 5.0                 | 6,000 <sup>a</sup> |
| Antimony   | 1.0                 | 60 <sup>^</sup>    |
| Arsenic    | 1.0                 | 25 <sup>^</sup>    |
| Cadmium    | 1.0                 | 75 <sup>^</sup>    |
| Cobalt     | 1.0                 | -                  |
| Copper     | -                   |                    |
| Lead       | -                   | 90 <sup>+</sup>    |
| Mercury    | 0.5                 | 60 <sup>^</sup>    |
| Molybdenum | 1.0                 | -                  |
| Zinc       | -                   |                    |

<sup>=</sup> State Limit: Draft practical quantitation limits as defined in the CSPA Rule Reporting Guidance, available at: [http://www.ecy.wa.gov/programs/swfa/cspa/pdf/cspaguide\\_pql.pdf](http://www.ecy.wa.gov/programs/swfa/cspa/pdf/cspaguide_pql.pdf), accessed 1/3/2012.

<sup>a</sup> Consumer Products Safety Improvement Act, establishes a total of 1,000 ppm for each of six phthalates, available at: <http://www.cpsc.gov/about/cpsia/faq/108faq.html#108q7>, accessed 1/24/2012.

<sup>^</sup> Federal Limit: ASTM F963-07, Maximum allowable amounts in surface coatings of toys.

<sup>+</sup> Federal Limit: 16 C. F. R. 1303 restrictions in surface coatings of consumer goods and children’s products. Non-soluble portions are limited to 100 ppm in August 2011.

**Table 2. Specific Phthalate Esters Included in the Study**

| <b>Phthalate</b>                 | <b>CAS Number</b> |
|----------------------------------|-------------------|
| Diethyl phthalate (DEP)          | 84-66-2           |
| Dibutyl phthalate (DBP)          | 84-74-2           |
| Di-n-Hexyl Phthalate (DHP)       | 84-75-3           |
| Butyl Benzyl phthalate (BBP)     | 85-68-7           |
| Di-2-ethylhexyl phthalate (DEHP) | 117-81-7          |
| Di-n-octyl phthalate (DnOP)      | 117-84-0          |
| Diisodecyl phthalate (DIDP)      | 26761-40-0        |
| Diisononyl phthalate (DINP)      | 28553-12-0        |

For screening purposes, products containing half or more of the state action levels in Table 1 will be forwarded to the laboratory for validation (to the limits of the laboratory budget). It should be noted, criteria under ASTM F963-07 and 16 C.F.R. § 1303 are designed for soluble portions of surface coatings. XRF screening, however, provides results for total metals. In the instance of more detectable levels of metal than the budget will allow, those product samples with the highest concentrations will be sent to the laboratory for additional analysis.

All 9 metals will be analyzed in each sample forwarded to the laboratory if screening levels for a single metal are violated. In addition to products that exceed the screening levels, multiple samples containing low levels will be forwarded to the laboratory for analysis.

As with metals, samples containing the highest levels of phthalates determined from available information such as labels, product databases and other readily-available information will be sent to the laboratory for analysis. The exact number of samples will depend upon the availability of applicable products and budgetary constraints.

## **Organization and Schedule**

Table 3 lists the individuals involved in the project and Table 4 contains a schedule.

**Table 3. Organization of Project Staff and Responsibilities**

| <b>Staff</b>                          | <b>Title</b> | <b>Responsibilities</b>  |
|---------------------------------------|--------------|--|
| Joshua Grice, W2R<br>(360) 407-6786   | Client       | Clarifies scopes of the project. Provides internal review of the QAPP and approves the final QAPP. |
| John Williams, W2R<br>(360) 407-6940  | Client       | Clarifies scopes of the project. Provides internal review of the QAPP and approves the final QAPP. |
| Ken Zarker, HWTR-HQ<br>(360) 407-6698 | Client       | Reviews project scope and budget, tracks progress, reviews draft QAPP and approves the final QAPP. |

| Staff   | Title           | Responsibilities  |
|---|-----------------|---|
| Alex Stone<br>HWTR-HQ Program<br>(360) 407-6758 | Project Manager | Writes QAPP, oversees field sampling and transportation of samples to laboratory. Conducts QA review of data, analyzes and interprets data. Writes draft report and final report. |
| Samuel Iwenofu<br>HWTR-SWRO<br>(360) 407-6964   | HWTR QA Officer | Reviews draft QAPP and approves final QAPP.   |
| Carol Kraege, W2R<br>(360) 407-6906             | Client          | Reviews project scope and budget, tracks progress, reviews the draft QAPP and approves final QAPP and expenditure of funds for implementation of the QAPP.                        |

HWTR-HQ: Hazardous Waste and Toxics Reduction Program-Headquarters.

HWTR-SWRO: Hazardous Waste and Toxics Reduction Program-Southwest Regional Office

QAPP: Quality Assurance Project Plan.

W2R: Waste 2 Resources.

**Table 4. Proposed Schedule for Completing Field and Laboratory Work and Reports**

| Field and laboratory work         | Due date      | Lead staff |
|-----------------------------------|---------------|------------|
| Field work completed              | March 2012    | Alex Stone |
| Laboratory analyses completed     | October 2012  |            |
| Final report                      |               |            |
| Author lead / Support staff       | Alex Stone    |            |
| Schedule                          |               |            |
| Draft due to supervisor           | November 2012 |            |
| Draft due to client/peer reviewer | December 2012 |            |
| Final (all reviews done)          | February 2013 |            |
| Final report due on web           | April 2013    |            |

## Sample Collection and Preparation

Products will be obtained in person or through internet retailers by HWTR or W2R staff. In addition, products reserved from other Ecology sampling events will be evaluated to determine if they meet the requirements of this QAPP.

Upon collection, products will be removed from their original packaging using pre-cleaned stainless steel implements. Products will be separated into to three fractions. Fraction 1 will consist of the product packaging that will be retained for possible analysis under a separate QAPP. Fraction 2 will comprise the product contents. Fraction 3 will consist of the container used to hold the product ingredients. If necessary, Fraction 3 may be further broken down into individual components as defined in CSPA rule reporting guidance documents. Products in Fraction 1 will be retained for possible analysis during other sampling events. Individual components of the product (Fraction 3) will be screened separately. Items with different colors

or base materials will be treated as components. Additionally, individual pieces of products intended to be disassembled will be treated as components.

Components targeted for testing will be removed with stainless steel tools (scissors, pliers, saws, etc.) for further testing. All tools will be cleaned following the sequence identified above. Those samples to be sent for both metals and phthalates analysis will be divided in half for possible shipment to different laboratories.

Some samples such as those consisting of hard plastic or other unique construction may be sent out for cryomilling to facilitate release of the chemicals of interest from the plastic matrix during extraction and sample preparation. Cryomilling refers to the process of reducing a sample to very small particle sizes by employing cryogenic temperatures and a mechanical mill. Milled samples will be screened by XRF in the stand. Cryomilling decisions will be made on a case-by-case basis. Non-plastic items such as foams, textiles and metals will be reduced in size using a file, drill, dremel tool or scissors. Scrapings will be further ground (if the material allows) by mortar and pestle. Sub-sampled materials (ground, cut or scraped) will be reanalyzed prior to laboratory testing. Ecology will issue a Request For Proposals (RFP) to identify a company who can cryomill these samples.

The samples will be screened for metals using the XRF. Packages that contain appreciable levels of metals will be sent to Manchester laboratory for analysis, where possible. If Manchester is unable to meet the QAPP requirements, the same procedure used for phthalate analysis will be used to obtain a contract laboratory to conduct the sample analysis.

Product samples will be sent to a contract laboratory for phthalate analysis. Laboratories under contract to the state to provide analytical data (State Contract 1807) will be approached first for analytical support. If no contract laboratory can conduct the analyses, the Project Manager will solicit qualified laboratories to provide analytical services. The Project Manager will be responsible for the review and evaluation of all laboratory analyses.

Photos and descriptive notes on each product screened such as approximate thickness, surface roughness, material makeup, etc. will be recorded. Other information such as the type of advertisement used to sell the product, where in the store the product was located, etc. may be necessary to prove the product was intended for children that fall within a given age group.

All field and laboratory staff handling the items will wear powder free nitrile gloves. Stainless steel tools used to deconstruct the product or remove it from its products along with the mortar and pestle will be cleaned by the following sequence: hot water scrub with liquinox soap, 10% nitric acid rinse, deionized water rinse, acetone rinse, and hexane rinse.

## Analytical Procedures

### XRF Analysis

Individual components of packaging will be screened using a Niton XL3t portable XRF gun (Figure 1) or equivalent following the manufacturers recommendations and adaptations of ASTM method F 2617-08 *Standard Test Method for Identification and Quantification of Chromium, Bromine, Cadmium, Mercury, and Lead in Polymeric Material Using Energy Dispersive X-ray Spectrometry*. The W2R program is currently in the process of purchasing an XRF instrument. Actual instrument details may vary depending upon the Model and Company selected from the bidding process.

For the initial screening, a reading will be taken for at least 30 seconds on a smooth (or near smooth) area of the packaging large enough to cover the spectrometer's window and at least 2 mm thick. If the item is less than 2 mm thick, it may be folded on to itself until 2 mm depth has been reached (care will be taken to trap minimal air in between folds).

If the screening measurement violates screening criteria, a second longer measurement will be taken (up to 180 seconds). Both measurements will be taken using the appropriate XRF software package (based on sample material). Detection limits are shown in Table 5. After XRF analyses are completed, samples will be placed in pre-cleaned I-Chem jars and forwarded to the appropriate laboratory for testing.



Figure 1. Niton Portable XRF

**Table 5. Niton Portable XRF LOQs and Expected Range of Results**

| Element    | Expected Range of Results (ppm) | LOQ (ppm) <sup>+</sup> |
|------------|---------------------------------|------------------------|
| Antimony   | <LOQ - 300                      | 25                     |
| Arsenic    | <LOQ - 300                      | 3                      |
| Cadmium    | <LOQ - 300                      | 15                     |
| Cobalt     | <LOQ - 300                      | 15                     |
| Copper     | <LOQ - 300                      | 15                     |
| Lead       | <LOQ - 300                      | 4                      |
| Mercury    | <LOQ - 10                       | 6                      |
| Molybdenum | <LOQ - 300                      | *                      |
| Zinc       | <LOQ - 300                      | 15                     |

ppm = parts per million

LOQ = Limit of Quantitation

<sup>+</sup> Polyethylene blank, 8 mm aperture, 180 second total analysis time

\* Detection limits are not specified by the manufacturer for these elements

All samples screened will be assigned a unique identifier and results from the XRF will be transferred to Microsoft Excel spreadsheets.

## Laboratory

Table 5 describes digestion and analysis methods along with estimated LOQ's. Metals samples will be prepared following EPA 3052 (microwave complete digestion) and measured using ICP-MS or CVAA (mercury).

Phthalates will be measured by a contract laboratory using GS-MS. Sample extraction and analysis methods used by the contract laboratory will be approved by the Project Manager. All sample extraction methods, however, must effect complete digestion of the sample.

**Table 6. Laboratory Methods and Reporting Limits**

| Analyte    | Digestion Method | Instrumentation | Method   | RL (ppm) |
|------------|------------------|-----------------|----------|----------|
| Antimony   | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Arsenic    | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Cadmium    | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Chromium   | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Cobalt     | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Copper     | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Lead       | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Molybdenum | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Mercury    | EPA 3052         | ICP-MS          | EPA 6020 | 0.1      |
| Zinc       | EPA 3052         | ICP-MS          | EPA 6020 | 1.0      |
| Phthalates | *                | GC-MS           | *        | 5.0      |

ICP-MS = Inductively-coupled plasma/mass spectrometry

CV AA = Cold vapor atomic absorption

GC-MS = Gas chromatography/mass spectroscopy

RL = Reporting Limit

\* Method will be approved by Project Manager but will be inline with CSPA PQL guidance.

## Budget

The project budget is included in Table 7.

**Table 7. Project Budget**

|              | # of Samples | Cost per sample | Total              |
|--------------|--------------|-----------------|--------------------|
| New Samples  | 100          | \$5.00          | \$500.00           |
| Metals       | 37           | \$200.00        | \$7400.00          |
| Phthalates   | 85           | \$350.00        | \$29,750.00        |
| <b>Total</b> |              |                 | <b>\$37,650.00</b> |

## Quality Objectives

Quality objectives for this project are to obtain data of sufficient quality so that the amount of metals and phthalates in children’s products can be determined. These objectives will be achieved through careful attention to the sampling, sample processing, measurement, and Quality Control (QC) procedures described in this plan.

### Measurement Quality Objectives

An XRF reading will be taken every 25 samples on standards provided by the manufacturer. Since the XRF analysis is being used as a screening tool only, no Measurement Quality Objectives (MQOs) are outlined. Performance of the portable XRF has been determined in a previous EAP report (Publication No. 12-03-009), which proves the efficacy of using XRF as a screening tool, particularly for metals. The conclusions from the report will be implemented in this work where possible and all screening will be done using a stand to minimize error.

MQOs for laboratory analysis of metals and phthalates are shown in Table 7. It is expected that MEL and contract laboratories will meet these criteria. MQOs falling outside of the acceptance limits will be reviewed by the Project Manager for their usability.

**Table 8. MQOs for Laboratory Analyses**

|            | <b>Laboratory<br/>Control Samples</b> | <b>Matrix<br/>Spikes</b> | <b>Duplicates<sup>+</sup></b> | <b>Method<br/>Blanks*</b> |
|------------|---------------------------------------|--------------------------|-------------------------------|---------------------------|
|            | (recovery)                            | (recovery)               | (RPD)                         | (ppm)                     |
| Antimony   | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Arsenic    | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Cadmium    | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Cobalt     | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Lead       | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Mercury    | 85- 115%                              | 75-125%                  | ±20%                          | 0.1                       |
| Molybdenum | 85- 115%                              | 75-125%                  | ±20%                          | 1.0                       |
| Phthalates | 70- 130%                              | 70-130%                  | ±20%                          | 30.0                      |

\* Metals reporting limits were established by raising soil limits by a factor of 10

<sup>+</sup> Matrix spike duplicates and split duplicates

RPD – Relative Percent Difference

ppm = parts per million

## Quality Control Procedures

### Field

No field quality control procedures are anticipated for this project.

### Laboratory

Table 8 shows laboratory QC samples planned for the project. Split duplicate samples will be used to assess variability in the data due to sample preparation and laboratory procedures.

**Table 9. Quality Control Tests**

|          | Laboratory Control Samples | Matrix Spikes | Matrix Spike Duplicates | Laboratory Duplicates | Split Duplicates <sup>†</sup> | Method Blanks | Surrogate Recovery* |
|----------|----------------------------|---------------|-------------------------|-----------------------|-------------------------------|---------------|---------------------|
| Elements | 1/batch                    | 1/batch       | 1/batch                 | 1/batch               | 1/batch                       | 1/batch       | every sample        |

<sup>†</sup> Dependent on amount of sample available

\* PBDEs only

## Data Management Procedures

XRF data from the screening portion of the project will be transferred to Microsoft Excel spreadsheets and managed by the Project Manager.

Data packages from MEL and any lab contracted selected for sample analysis will include case narratives discussing any problems encountered with the analyses, corrective actions taken, changes to the referenced method, and an explanation of data qualifiers. The narrative should address condition of the samples on receipt, sample preparation, methods of analysis, instrument calibration, recovery data, and results on QC samples. This information is needed to evaluate the accuracy of the data and to determine whether the MQOs were met.

### Audits

MEL and any contracted laboratory must participate in performance and system audits of their routine procedures. Results of these audits must be made available on request.

### Report

A final report detailing the findings of the study will be completed. The final report will include:

- Categorical descriptions of the products screened with the XRF (some information such as brands, product names, etc. will not be included).

- Comparison of laboratory results with XRF screenings, where applicable.
- Assessment of products test results from children's products for metals and phthalates.
- Determination of whether significant levels of phthalates are found in children's products.
- Data on specific children's products and product components and whether the levels of metals found would violate standards in the CSPA legislation.

## **Data Verification**

The Project Manager will conduct a review of all laboratory data generated by MEL and contract laboratories. The Project Manager will verify that methods and protocols specified in this QAPP were followed, that all calibrations, checks on quality control, and intermediate calculations were performed for all samples, and that the data are consistent, correct, and complete, with no errors or omissions. Evaluation criteria will include the acceptability of procedural blanks, calibration, matrix spike recoveries, labeled compound and internal standard recoveries, ion abundance ratios, duplicates, laboratory control samples, and appropriateness of data qualifiers assigned.

A case narrative will meet the requirements for a data verification report for MEL's chemical data.

## **Data Quality (Usability) Assessment**

The Project Manager will examine the data reviews, case narratives, and data packages to assess the usability of the data. To determine if project MQOs have been met, results for laboratory control samples, sample duplicates, matrix spikes, and labeled compound recoveries will be compared to QC limits. The method blank results will be examined to verify there was no significant contamination of the samples. To evaluate whether the targets for reporting limits have been met, the results will be examined for "non-detects" and to determine if any values exceed the lowest concentration of interest. Based on these assessments, the data will be either accepted, accepted with appropriate qualifications, or rejected and re-analysis considered.

## References

American Society for Testing and Materials (ASTM), 2008. F 2617-08 Standard Test Method for Identification and Quantification of Chromium, Bromine, Cadmium, Mercury, and Lead in Polymeric Material Using Energy Dispersive X-Ray Spectrometry.

Anderson, W.A., L. Castle, M. J. Scotter, R. C. Massey and C. Springall. 2001. *A biomarker approach to measuring human dietary exposure to certain phthalate diesters*. **Food Addit Contam**, 18, pages 1068-1074.

Centers for Disease Control and Prevention, 2009. Fourth National Report on Human Exposure to Environmental Contaminants. <http://www.cdc.gov/exposurereport/pdf/FourthReport.pdf>

Children's Safe Product Act, 2008. Chapter 70.240 RCW, available at: <http://apps.leg.wa.gov/rcw/default.aspx?cite=70.240&full=true>, accessed 1/23/2012.

Consumer Product Safety Commission (CPSC), 2007. Lead Testing by XRF Frequently Asked Questions. Business memo. Accessed 12/2010. <http://www.cpsc.gov/businfo/xrffaq.pdf>

CPSC, 2008. Consumer Product Safety Improvement Act, available at: <http://www.cpsc.gov/about/cpsia/legislation.html>, accessed 2/2012.

Ecology 2011. Control of Toxic Chemicals in Puget Sound: Assessment of Selected Toxic Chemicals in the Puget Sound Basin, 2007-2011. Accessed 1/26/12. <http://www.ecy.wa.gov/biblio/1103055.html>

Eisler, Ronald, 1993. Zinc Hazards to Fish, Wildlife, and Invertebrates: A Synoptic Review, U. S. Department of the Interior Fish and Wildlife Service, 126 pages. Available at: [http://www.pwrc.usgs.gov/infobase/eisler/chr\\_26\\_zinc.pdf](http://www.pwrc.usgs.gov/infobase/eisler/chr_26_zinc.pdf), accessed 1/23/2012.

Herrera Environmental Consultants, Inc., 2009. Recalculated Loading Rates by Land Use: Addendum 2 to the Phase 2 Toxics Loading Report, available at: <http://www.ecy.wa.gov/biblio/0810084addendum2.html>, accessed 1/23/2012.

Stone, Alex and Damon Delistraty, 2010, 'Sources of toxicity and exposure information for identifying chemicals of high concern to children', **Env. Impact Assess. Review**, 30, pages 380-387.

United States Food and Drug Administration (USFDA), Phthalate website at: <http://www.fda.gov/cosmetics/productandingredientsafety/selectedcosmeticingredients/ucm128042.htm>, accessed 1/3/2012.

Washington Department of Health (DOH), 2010. *Rationale for Reporting List of Chemicals of High Concern to Children Prepared by the Washington State Department of Health for the Children's Safe Product Act*, available at: <http://www.ecy.wa.gov/programs/swfa/rules/pdf/p1text.pdf>, accessed 1/3/2012.

## Appendices

### Appendix A. Chemicals of High Concern to Children

| CAS      | Chemical  |
|----------|---|
| 50-00-0  | Formaldehyde  |
| 62-53-3  | Aniline   |
| 62-75-9  | N-Nitrosodimethylamine  |
| 71-36-3  | n-Butanol   |
| 71-43-2  | Benzene   |
| 75-01-4  | Vinyl chloride  |
| 75-07-0  | Acetaldehyde  |
| 75-09-2  | Methylene chloride  |
| 75-15-0  | Carbon disulfide  |
| 78-93-3  | Methyl ethyl ketone   |
| 79-34-5  | 1,1,2,2-Tetrachloroethane   |
| 79-94-7  | Tetrabromobisphenol A   |
| 80-05-7  | Bisphenol A   |
| 84-66-2  | Diethyl phthalate   |
| 84-74-2  | Dibutyl phthalate (DBP)   |
| 84-75-3  | Di-n-Hexyl Phthalate  |
| 85-44-9  | Phthalic Anhydride  |
| 85-68-7  | Butyl Benzyl phthalate (BBP)  |
| 86-30-6  | N-Nitrosodiphenylamine  |
| 87-68-3  | Hexachlorobutadiene   |
| 94-13-3  | Propyl phthalate  |
| 94-26-8  | Butyl phthalate   |
| 95-53-4  | 2-Aminotoluene  |
| 95-80-7  | 2,4-Diaminotoluene  |
| 99-76-3  | Methyl phthalate  |
| 99-96-7  | p-Hydroxybenzoic acid   |
| 100-41-4 | Ethylbenzene  |
| 100-42-5 | Styrene   |
| 104-40-5 | 4-Nonylphenol; 4-NP and its isomer mixtures including CAS 84852-15-3 and CAS 25154-52-3 |
| 106-47-8 | para-Chloroaniline  |
| 107-13-1 | Acrylonitrile   |
| 107-21-1 | Ethylene glycol   |
| 108-88-3 | Toluene   |
| 108-95-2 | Phenol  |
| 109-86-4 | 2-Methoxyethanol  |
| 110-80-5 | Ethylene glycol monoethyl ester   |

| CAS        | Chemical  |
|------------|---|
| 115-96-8   | Tris(2-chloroethyl) phosphate   |
| 117-81-7   | Di-2-ethylhexyl phthalate (DEHP)  |
| 117-84-0   | di-n-octyl phthalate (DnOP)   |
| 118-74-1   | Hexachlorobenzene   |
| 119-93-7   | 3,3'-Dimethylbenzidine and Dyes Metabolized to 3,3'-Dimethylbenzidine                           |
| 120-47-8   | Ethyl phthalate   |
| 123-91-1   | 1,4-Dioxane   |
| 127-18-4   | Perchloroethylene   |
| 131-55-5   | Benzophenone-2 (Bp-2); 2,2',4,4'-Tetrahydroxybenzophenone                                       |
| 140-66-9   | 4-tert-Octylphenol; 1,1,3,3-Tetramethyl-4-butylphenol   |
| 140-67-0   | Estragole   |
| 149-57-5   | 2-Ethylhexanoic Acid  |
| 556-67-2   | Octamethylcyclotetrasiloxane  |
| 608-93-5   | Benzene, pentachloro  |
| 842-07-9   | C.I. Solvent Yellow 14  |
| 872-50-4   | N-Methylpyrrolidone   |
| 1163-19-5  | 2,2',3,3',4,4',5,5',6,6'-Decabromodiphenyl ether; BDE-209                                       |
| 1763-23-1  | Perfluorooctanyl sulphonic acid and its salts; PFOS   |
| 1806-26-4  | Phenol, 4-octyl-  |
| 5466-77-3  | 2-Ethyl-hexyl-4-methoxycinnamate  |
| 7439-97-6  | Mercury & mercury compounds including methyl mercury (22967-92-6)                               |
| 7439-98-7  | Molybdenum & molybdenum compounds   |
| 7440-36-0  | Antimony & Antimony compounds   |
| 7440-38-2  | Arsenic & Arsenic compounds including arsenic trioxide (1327-53-3) & dimethyl arsenic (75-60-5) |
| 7440-43-9  | Cadmium & cadmium compounds   |
| 7440-48-4  | Cobalt & cobalt compounds   |
| 25013-16-5 | Butylated hydroxyanisole; BHA   |
| 25154-52-3 | Nonylphenol   |
| 25637-99-4 | Hexabromocyclododecane  |
| 26761-40-0 | Diisodecyl phthalate (DIDP)   |
| 28553-12-0 | Diisononyl phthalate (DINP)   |

## Appendix B. Glossary, Acronyms, and Abbreviations

### Acronyms and Abbreviations

Following are acronyms and abbreviations used frequently in this report.

|         |  |
|---------|--|
| CDC     | Center for Disease Control and Prevention        |
| CHCC    | Chemicals of High Concern to Children            |
| e. g.   | For example                                      |
| Ecology | Washington State Department of Ecology           |
| et al.  | And others                                       |
| HQ      | Headquarters                                     |
| HWTR    | Hazardous Waste and Toxics Reduction Program     |
| i. e.   | In other words                                   |
| MEL     | Manchester Environmental Laboratory              |
| MQO     | Measurement quality objective                    |
| PBT     | persistent, bioaccumulative, and toxic substance |
| QA      | Quality assurance                                |
| RPD     | Relative percent difference                      |
| RSD     | Relative standard deviation                      |
| SOP     | Standard operating procedures                    |
| SRM     | Standard reference materials                     |
| SWRO    | Southwest Regional Office                        |
| W2R     | Waste 2 Resources Program                        |

### *Units of Measurement*

|       |   |
|-------|---|
| ng    | nanogram, a unit of mass equal to one millionth of a gram         |
| mg    | milligram, one thousandth of a gram                               |
| g     | gram, a unit of mass  |
| kg    | kilograms, a unit of mass equal to 1,000 grams.                   |
| meter | meter, a unit of distance   |
| mm    | millimeter, a unit of distance equal to one thousandth of a meter |
| Liter | liter, a unit of volume   |
| mL    | milliliter, equal to one thousandth of a liter                    |
| ppm   | parts per million   |
| mg/kg | milligrams per kilogram (parts per million)                       |
| ng/g  | nanograms per gram (parts per billion)                            |
| ng/kg | nanograms per kilogram (parts per trillion)                       |
| mg/L  | milligrams per Liter (parts per million)                          |
| ng/L  | nanograms per Liter (parts per trillion)                          |
| s.u.  | standard units  |